


	<b>QUALITÄTSMANAGEMENT</b>  <b>HANDBUCH</b>	Anforderungsprofil
		Formblatt: Fb_ 8 Dynamic
<i>Qualitätsmanagementsystem</i>  <b>technical datasheet</b>		Erarbeitet: 01 Juli 2009  Revi: 5

# Dynamic

## 1. Product description

- |                            |   |
|----------------------------|---|
| 1.1. Format                | 1380 x 193 x 8 mm   |
| 1.2. Packing               | 8 boards each pack = 2,131 m <sup>2</sup>   |
| 1.3. Technical description |   |
| - Surface                  | Three-dimensional interlaced melamine resin   |
| - Decor                    | Melamine resin impregnated printed paper  |
| - Core layer               | HDF High Density Fiberboard   |
| - Balance film             | Melamine resin impregnated paper  |
| 1.4. Installation          | Mechanical locking system , Clic-System – much easier to install , up to 50% quicker to install (against other clic systems). Floating installation according to the installation description . |
| 1.5. Classification        | EN 685 class 23 : heavy domestic use<br>class 32 : general commercial use<br><br>EN 14041 CE – Mark   |
| 1.6. Fire classification   | EN 13501 C <sub>fl</sub> – s1 (Hardly inflammable ~ B1)   |
| 1.7. Emission              | E1 lower than 0,05 ppm  |
| 1.8. Slip resistance       | Technical class DS  |
| 1.9. Thermal conductivity  | Thermal resistance according to DIN EN 12667 R= 0,0587 [(m <sup>2</sup> * K)/W]   |



# Dynamic

	Characteristic	Requirements	Unit	Testmethod
1.	Sampling			EN 13329
2.	Thickness	8	mm	EN 13329
3.	Level of use	21 - 32		EN 13329
4.	Wear resistance	AC4		EN 13329
5.	Impact resistance	IC2		EN 13329
6.	Thickness swelling 24h	≤ 18	%	EN 13329
7.	Resistance to staining	5,g. 1-2 4,g. 3		EN 438-2
8.	Internal bond	> 1,2	N/mm <sup>2</sup>	EN 319
9.	Surface soundness	> 1,5	N/mm <sup>2</sup>	EN 311
10.	Resistance to cigarette burns	4 no visible change		EN 424
11.	Surface layer width	± 0,1	mm	EN 13329
12.	Surface layer length	± 0,3	mm	EN 13329
13.	Squareness	max 0,2	mm	EN 13329
14.	Surface layer straightness	< 0,3	mm/m	EN 13329
15.	Height difference between elements	max 0,15	mm	EN 13329
16.	Openings between elements	max 0,2	mm	EN 13329
17.	Formaldehyd content	<0.05	ppm	EN 717-1

Erstellt (Datum, Unterschrift)  QS	Geprüft und Freigegeben (Datum, Unterschrift)  03.09.2014 Schmaltz	
---	---	--